

BALACRON

COVERS

Product datasheet

Collection : Textile
Design: : Mondial metallic

Composition		Dimensions	Test method
Base material	100% cotton, without backingpaper		
Warp	35,5	tex	
	18,5	picks/cm	EN 1049-2
Weft	50	tex	
	17,5	picks/cm	EN 1049-2
Total weight	250 ± 10	g/m ²	EN ISO 12127
Thickness	0,33 ± 0,03	mm	EN ISO 5084

Properties		Dimensions	Test method
Tensile strength			
Warp	> 400	N/50 mm	
Weft	> 400	N/50 mm	EN ISO 13934-1
Elongation at break			
Warp	< 10	%	
Weft	< 25	%	EN ISO 13934-1
Flexibility			
Warp	150 - 350	mN	
Weft	100 - 250	mN	DIN 53121
Abrasion Resistance	< 15	mg	EN ISO 5470-1
Foil blocking	++		Platex
Blocking	≤1		EN 25978
Lightfastness	6 - 8		EN ISO- 105-B 02
Standard measurement	(L) 50 meter X (W) 107 cm		
Last revised productsheet	11-04-12		
Revision state	06		

Balacron international BV

Rokerijweg 5
1271 AH Huizen
The Netherlands
Tel +31 35 524 84 25
Mail info@balacron.com
Web www.balacron.com