

BALACRON

COVERS

Product datasheet

Collection : Textile
Design: : Ottawa

Composition		Dimensions	Test method
Base material	100% FSC™ Rayon laminated on 40 g/m2 FSC™ Basepaper		
Warp	20	tex	
	24	picks/cm	EN 1049-2
Weft	20	tex	
	21	picks/cm	EN 1049-2
Total weight	155 ± 10	g/m2	EN ISO 12127
Thickness	0,30 ± 0,03	mm	EN ISO 5084
Properties		Dimensions	Test method
Tensile strength			
Warp	> 250	N/50 mm	
Weft	120	N/50 mm	EN ISO 13934-1
Elongation at break			
Warp	< 15	%	
Weft	< 20	%	EN ISO 13934-1
Flexibility			
Warp	350 - 750	mN	
Weft	100 - 300	mN	DIN 53121
Foil Blocking			
	+		Platex
Lightfastness	4 - 6		EN ISO-105-B 02
Certifications	FSC® certified: FSC-C141806		
Standard measurement	(L) 100 meter X (W) 132 cm		
Last revised productsheet	18-04-16		
Revision state	02		

Balacron international BV

Rokerijweg 5
1271 AH Huizen
The Netherlands
Tel +31 35 524 84 25
Mail info@balacron.com
Web www.balacron.com

